



## POLYURETHANE ARCHITECTURAL MEMBRANE

Base Fabric Type (Scrim)	Polyester
Adhesion ASTM D4431	20lbs (lbs/2in)
Finish Weight Method ASTM D3776	20 oz./sq.yd. (+/- 5%)
Surface Protection	Acrylic Top Coat (Rain Kleen)
Tongue Tear (lbs) Method ASTM D2261	W175/F155lbs
Grab Tensile Method ASTM D5034	W450/F345lbs/in
Strip Tensile 1" FED-STD-191A Method 5102	W325/F245lbs/in
Hydrostatic Burst ASTM D751/A	R600+ F600+
Cold Crack FED-STD-191A Method 5874	Pass -40° F

### FIRE RATINGS

1. NFPA 701
2. ASTM E84
3. California State Fire Marshall
4. CAN/ULC-S-109
5. CAN/ULC-S-102

Flame Spread Index <25  
Smoke Development rating <450