



## DUPONT TEDLAR® COATED ARCHITECTURAL MEMBRANE

Base Fabric Type (Scrim)	Polyester
Base Fabric Weight (Scrim)	4.3 oz/sq. yd.
Finish Coated Weight Method 5041	24.0 oz /sq.yd. (+/-2)
Surface Protection	Tedlar ® PVF Film
Tongue Tear Method ASTM D751 8" x 10" sample size	140/130 lbf
Trapezoid Tear Method ASTM D4533	80/65 lbf
Grab Tensile Method ASTM D751	400/350 lbf
Strip Tensile Method ASTM D751 Procedure B	300/240 lbf/in
Hydrostatic Resistance Method ASTM D751 Procedure A	500 psi
Dead Load Room Temperature 160°F / 71°C ASTM D751	1 - 1/2" seam 120 lbf 60 lbf
Low Temperature ASTM D2136	LTC 1/3" mandrel, 4hr Pass @ -40°F
Adhesion ASTM 0751	10lbf/in

### FIRE RATINGS

- 1 California State Fire Marshal
- 2 National Fire Protection Association - 701
- 3 ASTM E84
- 4 CAN/ULC-S-109
- 5 CAN/ULC-S-102

Flame Spread Index <25  
Smoke Development Rating <450